

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09D 11/00, C09B 67/22, 67/20	A1	(11) International Publication Number: WO 99/61534 (43) International Publication Date: 2 December 1999 (02.12.99)
(21) International Application Number: PCT/US99/11935 (22) International Filing Date: 28 May 1999 (28.05.99) (30) Priority Data: 60/087,011 28 May 1998 (28.05.98) US (71) Applicant (for all designated States except US): SUN CHEMICAL CORPORATION [US/US]; 222 Bridge Plaza South, Fort Lee, NJ 07024 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): ORTALANO, Darren, Mark [US/US]; 4056 Crystal Creek Drive, Cincinnati, OH 45245 (US). VISSING, Christopher, Joseph [US/US]; Apartment 10, 12 Montgomery Way, Amelia, OH 45012 (US). (74) Agent: PERSLEY, Sidney; 222 Bridge Plaza South, Fort Lee, NJ 07024 (US).		(81) Designated States: CA, MX, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: DYE BASED AQUEOUS PIGMENT DISPERSIONS (57) Abstract Aqueous based pigment dispersions wherein the pigment is dispersed in a dye in the absence of any other dispersant or additive. Aqueous based printing ink compositions containing these pigment dispersions. Methods for preparing aqueous based pigment dispersions, wherein the pigment is dispersed in a dye, and for preparing printing ink compositions incorporating these dispersions.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

DYE BASED AQUEOUS PIGMENT DISPERSIONS

BACKGROUND OF THE INVENTION

Field of the Invention

The present invention is directed to aqueous based pigment dispersions and ink compositions containing same wherein the pigment is dispersed in a dye in the absence of surfactants or resins.

Description of Related Art

Aqueous based pigment dispersions are used in a variety of industrial applications such as the manufacture of printing ink, paint, pulp and paper, coatings, and textiles to provide coloration. Inks and coatings typically contain clear extenders which generally consist of resins and additives which are suitable for the specific application. The resins and additives employed cause the pigment to adhere to the surface of the substrate being colored. Since dispersed pigments typically have fine particle sizes, one only needs to provide minimal agitation to establish coloration. Therefore, the use of dispersed pigments are convenient for color formulators.

The more common employed pigment dispersants include styrene/acrylic copolymers, acrylic polymers, polyvinyl pyrrolidone resins, octylphenol ethoxylates, acetylenics, phosphate esters, and sulfonates. There are other commercially available pigment dispersants some of these are described in the Directory on Emulsifiers and Detergents, Volume 1: Emulsifiers and Detergents, MC Publishing Co., Glen Rock, NJ. The choice of dispersant or class of dispersants for an aqueous pigment dispersion will depend on the end-use intended for the aqueous pigment dispersion. The pigment employed is typically hydrophobic and therefore insoluble in water. However, the dispersant may have both hydrophobic and hydrophilic properties. In an aqueous based dispersions, the hydrophobic portion of the dispersant attaches to the pigment

5 while the hydrophilic portion resides in the aqueous phase of the dispersion. The hydrophobic portion (hydrophile) of the dispersant can be anionic, nonionic or cationic. Anionic or nonionic hydrophiles are more commonly used in the printing, ink, paint, textile and pulp and paper industries. For example, various printing ink applications, especially film printing applications, typically require the use of styrene/acrylic resin
10 pigment dispersants. On the other hand, in textile applications non-ionic surfactant pigment dispersants are used.

The use of styrene/acrylic resins and surfactants presents a number of drawbacks when aqueous pigment dispersions are used, for example, in ink jet printing and pulp and paper applications. When used in pulp and paper applications,
15 such use can lead to foaming which, consequently can cause defects in the paper, e.g. mottling. Foaming itself has a negative effect on pulp and paper production. In thermal cure ink jet applications, the use of resins and surfactants can clog the ink jet printing head as these components sometimes break up to form water-insoluble fragments which adhere to the interior nozzle of the print head. In addition, high surface tensions
20 are normally required for ink jet inks in order to achieve reduced dot gain in the printed product. Due to their nature, however, surfactants tend to lower the surface tension of inks. Color gamut is another key parameter employed to measure inking systems, however, many surfactants, such as lignosulfonates, are darkly colored and therefore can detract from the colorization by the pigment.

25 As the aforementioned problems clearly illustrate, the use of surfactants and resins introduce a number of drawbacks related to the use of conventional aqueous pigment dispersions in industrial printing applications. Therefore, finding a dispersant that addresses these problems has become an important industry objective. Industrial initiatives presently ongoing are aimed at developing aqueous pigment dispersions for
30 paper and pulp and ink jet printing applications that overcome these drawbacks. In the meantime, the paper and pulp and ink jet printing industries employ dyes or dye based pigments for coloration. Dyes will continue to be heavily used as colorants in these industries until the problems associated with pigmented systems have been resolved.

Improving the lightfastness of printed materials continues to be a primary
35 objective for the large format printing market (i.e. billboards and posters). Likewise,

5 paper mills seek to adopt pigment colorants for the improved lightfastness they offer. Doing so would offer manufacturing advantages such as eliminating the need for filtration systems to remove the excess dye from manufacturing waste streams. Moreover, the lightfastness of dye based materials is limited and improvements in this area have been slow in coming. The pulp and paper industry also uses low-end
10 pigments such as OT Yellow and C.I. Pigment Yellow 14 for various applications. These pigments, however, only offer slightly improved lightfastness properties.

The general specification for pigments suitable for use in industrial applications include the obvious requirements of daylight resistance, alkali, acid, and heat resistance and the wettability of the pigment by the vehicle selected. Pigments to be dispersed in
15 aqueous vehicles are chosen for their flow characteristics, gloss level and printability. Dispersion stability is also important. Additional physical and economic requirements for the pigment is that it have low oil absorption, high color strength and be economically priced.

Dyes are fundamentally different from pigments as they are normally pure
20 organic or metallo organic complexes which are generally soluble in the medium they color. For instance, water soluble dyes are often used in aqueous based applications. The color or tinting strength of a pigment or dye is a measure of its ability to impart color to a system. Dye color is produced by selective absorption. No discrete particles are present, no scatter occurs and the system is transparent. By contrast, pigment color is
25 primarily related to its chemical composition, particle size and distribution. The actual color strength, in the case of a pigmented printing ink will depend upon film thickness and the concentration of the pigment. Dyes, once dissolved, are generally present as single molecules, while pigments are deaggregated to primary particles or crystals and dispersed into a medium, a process that typically requires high energy to effect suitable
30 coloration. Primary pigment particles are composed of many thousands of molecules packed into a concentrated area having a dimension of 50 to 500 nanometers. These primary particles can be amorphous or crystalline. Dye based inks are widely used on paper for bread wrappers, bags, etc. where no lightfastness requirement is demanded. Because of their almost Newtonian behavior, low viscosity inks of high color strength
35 may be formulated enabling clean printing to be obtained. The migration tendencies of

5 dyes do not encourage their use on plastic films or in contact with a wide range of products. Due perhaps to their differences, the use of dyes and pigments have generally been mutually exclusive to one another. An exception is the use of dyes to form dye based pigment like materials (e.g. laked pigments such as FD&C Red No. 6, C.I. Pigment Red 81 and C.I. Pigment Violet 3). The lightfastness of a dye may be
10 improved, for example, by using a high acid value phenolic type resin in place of, or in combination with, tannic acid, reducing the amount of resin required; a technique known as "laking". Laking can affect the shade or coloration of the dye considerably. The lightfastness of dye based ink formulations is substantially less by comparison than that of pigment based ink formulations.

15 U.S. Patent 3,477,866 discloses the use dyes to form dye based pigments formed from the salts of acid dyes dispersed in water using conventional surfactants and resins. U.S. Patent 4,162,348 discloses the use of anionic surfactants to disperse a pigment and a dye. The two dispersions are then combined to form a single colorant. U.S. Patent 4,468,230 relates to dispersions of anionic acid dyes having limited
20 solubility using conventional surfactants. U.S. Patent 4,523,953 describes dyes co-precipitated with titanium dioxide or aluminum hydroxide pigments to form pigment complexes. These complexes are then dispersed in water, or some other medium, by conventional dispersants. U.S. Patent 4,664,711 relates to dyes used to provide color for ink pen formulations. No pigments are discussed since generally ink pen
25 formulations do not use pigments. U.S. Patent 5,735,941 teaches using of separate cartridges of an anionic stabilized a pigment based formulation and a dye-based formulation made of a cationic dye. When the two are jetted next to one another the anionic stabilized pigment reduces intercolor bleeding. The patent illustrates the synergistic use of pigments and dyes to solve an important problem in industrial ink jet
30 applications (i.e. intercolor bleeding). European Patent 0 745 651 discloses the use of dye based ink jet formulations and describes the many problems associated with the use of conventional dispersants. Finally, the American Ink Maker, June 1997 Edition, features two articles entitled Ink Jet Technology (pgs. 36 to 39) and Pigmented Inks for Ink Jet Systems (pgs. 23 to 24 and 80) which relate to the separate use of dyes and
35 pigments. The articles represent the widely accepted view held by the skilled artisan

5 that these components should be used individual as colorants. More specifically they teach that aqueous pigment dispersions are to used exclusive of dyes.

It is an object of the present invention to provide aqueous based pigment compositions employing dye as the dispersant which shall be advantageously suitable for overcoming the aforementioned problems associated with conventional aqueous
10 pigment dispersions.

SUMMARY OF THE INVENTION

15 The invention is aqueous based pigment dispersion wherein the pigment is dispersed in a dye in the absence of any other dispersant or additive.

In another aspect, the invention is aqueous based printing inks containing a pigment dispersion wherein the pigment is dispersed in a dye.

In yet another aspect, the invention is a method of preparing aqueous based
20 pigment dispersions and a method for preparing aqueous based printing inks that incorporate pigment dispersions wherein the pigment is dispersed in a dye.

DETAILED DESCRIPTION OF THE INVENTION

25 The aqueous based pigment dispersions and ink compositions of the present invention do not contain surfactant or resins and thereby avoid the problems associated with the use of these components without any loss in color gamut. In addition, a lower particle size distribution than that achieved using conventional surfactant dispersants is generally produced by the present invention. It has also been surprisingly found that the
30 use of dyes as a pigment dispersant: (a) reduces and/or eliminates nozzle clogging in printing heads; (b) prevents surface tension reduction in formulated printing inks; (c) reduces the tendency for foaming; (d) sustains or increases the color gamut and cleanliness of the color shade obtainable; (e) avoids the negative effect on color caused by the use of surfactants; (f) increases lightfastness over that achievable with
35 dye colorants; and (g) generally reduces the particle size distribution of the dispersed

5 pigment. There are also the advantages for the formulators as they are able to achieve improved lightfastness. In addition, manufacturers are able to reduce dye emissions in manufacturing process waste streams.

The classes of dyes suitable for use in present invention may be selected from acid dyes, natural dyes, direct dyes (either cationic or anionic), basic dyes, and reactive
10 dyes.

The acid dyes, also regarded as anionic dyes, are soluble in water and mainly insoluble in organic solvents and may be selected, from yellow acid dyes, orange acid dyes, red acid dyes, violet acid dyes, blue acid dyes, green acid dyes, and black acid dyes. European Patent 0 745 651, incorporated herein by reference, describes a
15 number of acid dyes which are suitable for use in the present invention. The yellow acid dyes selected include Acid Yellow 1 (C.I. 10316); Acid Yellow 7 (C.I. 56205); Acid Yellow 17 (C.I. 18965); Acid Yellow 23 (C.I. 19140); Acid Yellow 29 (C.I. 18900); Acid Yellow 36 (C.I. 13065); Acid Yellow 42 (C.I. 22910); Acid Yellow 73 (C.I. 45350); Acid Yellow 99 (C.I. 13908); Acid Yellow 194; and Food Yellow 3 (C.I. 15985). The orange
20 acid dyes selected include Acid Orange 1 (C.I. 13090/1); Acid Orange 10 (C.I. 16230); Acid Orange 20 (C.I. 14603); Acid Orange 76 (C.I. 18870); Acid Orange 142; Food Orange 2 (C.I. 15980); and Orange B. The red acid dyes selected include Acid Red 1 (C.I. 18050); Acid Red 4 (C.I. 14710); Acid Red 18 (C.I. 16255); Acid Red 26 (C.I. 16150); Acid Red 27 (C.I. 16185); BASOVIT™ 425E (available from BASF Corporation)
25 a xanthene based acid dye also known as Acid Red 51 (C.I. 45430); Acid Red 52 (C.I. 45100); Acid Red 73 (C.I. 27290); Acid Red 87 (C.I. 45380); Acid Red 94 (C.I. 45440); Acid Red 194; and Food Red 1 (C.I. 14700). The violet acid dyes selected include Acid Violet 7 (C.I. 18055); and Acid Violet 49 (C.I. 42640). The blue acid dyes selected include Acid Blue 1 (C.I. 42045); Acid Blue 9 (C.I. 42090); Acid Blue 22 (C.I. 42755);
30 Acid Blue 74 (C.I. 73015); Acid Blue 93 (C.I. 42780); and Acid Blue 158A (C.I. 15050). The green acid dyes selected include Acid Green 1 (C.I. 10028); Acid Green 3 (C.I. 42085); Acid Green 5 (C.I. 42095); Acid Green 26 (C.I. 44025); and Food Green 3 (C.I. 42053). The black acid dyes selected include Acid Black 1 (C.I. 20470); Acid Black 194 (BASANTOL™ X80, available from BASF Corporation, an azo/1:2 CR-complex.

35 The direct dyes selected for use in the present invention include Direct Blue 86

5 (C.I. 74180); Direct Blue 199; Direct Black 168; Direct Red 253; and Direct Yellow 107/132 (C.I. Not Assigned). The direct dyes are commonly used in coloration of pulp paper.

The natural dyes selected for use in the present invention include Alkanet (C.I. 75520,75530); Annatto (C.I. 75120); Carotene (C.I. 75130); Chestnut; Cochineal (C.I. 75470); Cutch (C.I. 75250, 75260); Divi-Divi; Fustic (C.I. 75240); Hyperic (C.I. 75280); Logwood (C.I. 75200); Osage Orange (C.I. 75660); Paprika; Quercitron (C.I. 75720); Sanrou (C.I. 75100); Sandal Wood (C.I. 75510, 75540, 75550, 75560); Sumac; and Tumeric (C.I. 75300).

15 The reactive dyes selected for use in the present invention include Reactive Yellow 37 (monoazo dye); Reactive Black 31 (disazo dye); Reactive Blue 77 (phthalocyanine dye) and Reactive Red 180 and Reactive Red 108 dyes.

Preference is given to the use of acid dyes such as Acid Black 194, Acid Red 51, Acid Blue 9, Acid Green 26, Acid Yellow 36, Acid Orange 142, Direct Blue 86, Direct Red 253 and Direct Yellow 107/132 dyes. The aqueous based pigment compositions of invention comprise about 1 wt. % to about 50 wt.% dye, based on the total weight of the composition, and preferably comprise about 3 wt. % to about 25 wt.% dye.

Pigments suitable for use in the present invention may be selected from C.I. Pigment Black 1, C.I. Pigment Black 31, C.I. Pigment Black 11, C.I. Pigment Black 7, C.I. Pigment Blue 61, C.I. Pigment Blue 62, C.I. Pigment Blue 15, C.I. Pigment Blue 15:1, C.I. Pigment Blue 15:2, C.I. Pigment Blue 15:3, C.I. Pigment Blue 15:4, C.I. Pigment Blue 15:6, C.I. Pigment Blue 16, C.I. Pigment Blue 29, C.I. Pigment Blue 27, C.I. Pigment Green 17, C.I. Pigment Green 18, C.I. Pigment Green 7, C.I. Pigment Green 36, C.I. Pigment Orange 5, C.I. Pigment Orange 13, C.I. Pigment Orange 16, C.I. Pigment Orange 34, C.I. Pigment Orange 36, C.I. Pigment Violet 3, C.I. Pigment Violet 27, C.I. Pigment Violet 23, C.I. Pigment Violet 19, C.I. Pigment Red 122, C.I. Pigment Red 202, C.I. Pigment Red 206, C.I. Pigment Red 207, C.I. Pigment Red 22, C.I. Pigment Red 23, C.I. Pigment Red 17, C.I. Pigment Red 210, C.I. Pigment Red 170, C.I. Pigment Red 188, C.I. Pigment Red 185, C.I. Pigment Red 146, C.I. Pigment Red 144, C.I. Pigment Red 101, C.I. Pigment Red 176, C.I. Pigment Red 48:1, C.I. Pigment Red 48:2, C.I. Pigment Red 48:3, C.I. Pigment Red 49:1, C.I. Pigment Red 49:2, C.I.

5 Pigment Red 57:1, C.I. Pigment Red 81:1, C.I. Pigment Red 81:2, C.I. Pigment Red 81:3, C.I. Pigment Red 81:5, C.I. Pigment Red 179, C.I. Pigment Red 3, C.I. Pigment Red 249, C.I. Pigment Red 114, C.I. Pigment Red 181, C.I. Pigment Yellow 1, C.I. Pigment Yellow 2, C.I. Pigment Yellow 3, C.I. Pigment Yellow 147, C.I. Pigment Yellow 142, C.I. Pigment Yellow 42, C.I. Pigment Yellow 151, C.I. Pigment Yellow 154, C.I. 10 Pigment Yellow 180, C.I. Pigment Yellow 138, C.I. Pigment Yellow 139, C.I. Pigment Yellow 93, C.I. Pigment Yellow 109, C.I. Pigment Yellow 110, C.I. Pigment Yellow 14, C.I. Pigment Yellow 12, C.I. Pigment Yellow 17, C.I. Pigment Yellow 13, C.I. Pigment Yellow 74, C.I. Pigment Yellow 73, C.I. Pigment Yellow 75, C.I. Pigment Yellow 83, C.I. Pigment Yellow 65, C.I. Pigments Yellow 128, D&C Red No. 7, D&C Red No. 6 and 15 D&C Red No. 34. Preferably, the pigment employed in the present invention is a carbon black pigment such as Regal 330 (available from Cabot Corporation); quinacridone pigment such as Quinacridone Magenta (228-0122) (available from Sun Chemical Corporation, Fort Lee, NJ); diarylide yellow pigment such as AAOT Yellow (274-1788) (available from Sun Chemical Corporation); and phthalocyanine blue 20 pigment such as Blue 15:3 (294-1298) (available from Sun Chemical Corporation). The aqueous based pigment compositions of invention comprise about 1 wt. % to about 50 wt.% pigment, based on the total weight of the composition, and preferably comprise about 5 wt. % to about 50 wt.% pigment.

The water used in the present invention is pure or ultrapure water such as ion- 25 exchange water or water purified by ultrafiltration, reverse osmosis or distillation. Water sterilized by ultraviolet irradiation or by the addition of hydrogen peroxide, or the like, is preferred as it can prevent mold and bacteria growth during storage of the pigment dispersion over long periods of time. The amount of water added to the composition makes up the weight balance of the composition.

30 Additives may be used in combination with the dye and pigment of the present invention. For instance, ammonia or some other suitably functional amine may be used to adjust the pH of the dispersion. Biocides, such as Proxel GXL (available from Rohm & Haas, Philadelphia, PA) can be used to aid in the inhibition of bacterial growth. Glycols may be used to modify the properties of the dispersion and improve jettability 35 and would preferably include propylene glycol, polyethylene glycol (such as PEG 200,

5 400 and 1000, available from Union Carbide, Danbury, CT). Defoamers, co-solvents and surface active agents, such as octylphenoethoxylates or acetylenics, may be used to modify surface tension. However, additives are used the amount of additive should be held to a minimum. For example, a glycol should represent no more than 20 wt. % of the composition; a biocide no more than 0.5 wt. %; a defoamer no more than 1.5 wt. %; and a co-solvent no more than 30 wt.%.
10

In addition, emphasis is given to the fact that the individual pigment and dye components of the dispersions and ink compositions of the present invention may be combined as desired and may be selected from those having the same or different color space.

15 In order to illustrate the effectiveness of the aqueous based pigment compositions of the present invention, conventional aqueous based pigment compositions containing surfactants, such as a phosphate ester surfactant (available from Rhone Poulenc, Cranbury, NJ); Maracarb N-1 (available from Lignotech, Greenwich, CT); and PEG-400 a polyethylene glycol (available from Union Carbide, Corporation), along with resins were prepared for comparison.
20

The following examples illustrate specific aspects of the present invention and are not intended to limit the scope thereof in any respect and should not be so construed. The temperatures are in degrees centigrade and the percentages are by weight unless otherwise indicated.

25 Example 1

C.I. Pigment Blue 15:3 (20 wt. %, Green/Shade Phthalocyanine Blue) was dispersed into distilled water (70 wt.%) with Acid Blue 9 dye (10 wt.%, Triphenylmethane Blue dye, Basacid™, NB-755 available from BASF Corporation) for 18 minutes on an Eiger™ mill.
30

Example 2

C.I. Pigment Blue 15:3 (24 wt. %, Green/Shade Phthalocyanine Blue, 249-1282 available from Sun Chemical) was dispersed into distilled water (70 wt.%) with Direct Blue 86 dye (6 wt.%, Phthalocyanine dye, SANDOVOC-L™ Turquoise GL Liquid 041, available form Clariant Corporation, Leeds, U.K.) for 18 minutes on an Eiger™ mill.
35

Example 3

C.I. Pigment Blue 15:3 (24 wt. %, Green/Shade Phthalocyanine Blue, 249-1290 available from Sun Chemical) was dispersed into distilled water (68 wt. %) with Direct Blue 86 dye (8 wt. %, Phthalocyanine dye, SANDOVOC-L™ Turquoise GL Liquid 041, available from Clariant Corporation) for 18 minutes on an Eiger™ mill.

Example 4

C.I. Pigment Blue 15:3 (20 wt. %, Green/Shade Phthalocyanine Blue, 249-1298, available from Sun Chemical) was dispersed into distilled water (70 wt. %) with Direct Blue 199 dye (10 wt. %, Phthalocyanine dye, SANDOVOC-L™ Br. Blue GNS Liquid, available from Clariant Corporation) for 18 minutes on an Eiger™ mill.

Example 5

C.I. Pigment Blue 15:3 (20 wt. %, Green/Shade Phthalocyanine Blue, 249-1298, Sun Chemical) was dispersed into distilled water (70 wt. %) with Direct Blue 199 dye (10 wt. %, Phthalocyanine dye, SANDOVOC-L™ Br. Blue GNS Liquid, available from Clariant Corporation) for 25 minutes on an Eiger™ mill.

Example 6

C.I. Pigment Blue 15:3 (14 wt. %, Green/Shade Phthalocyanine Blue, 249-1290 available from Sun Chemical) was dispersed into distilled water (72 wt. %) with Direct Blue 199 dye (14 wt. %, Phthalocyanine dye, SANDOVOC-L™ Br. Blue GNS Liquid, available from Clariant Corporation) for 30 minutes on an Eiger™ mill.

Example 7

C.I. Pigment Blue 15:3 (20 wt. %, Green/Shade Phthalocyanine Blue, 249-1290, available from Sun Chemical) was dispersed into distilled water (60 wt. %) with Direct Blue 199 dye (10% Phthalocyanine dye, SANDOVOC-L™ Br. Blue GNS Liquid, available from Clariant Corporation) and polyethylene glycol (10 wt. %, PEG-400) for 18 minutes on an Eiger™ mill.

Example 8

(COMPARATIVE)

C.I. Pigment Blue 15:3 (35 wt. %, Green/Shade Phthalocyanine Blue, 249-1298 available from Sun Chemical) was dispersed into water (56 wt. %) with an ammonia solubilized styrene/acrylic copolymer (9 wt. %, Joncryl™ 67, available from S.C.

Johnson Polymer Corp., Racine, WI) on an Eiger™ mill for 18 minutes.

Example 9

C.I. Pigment Green 7 (20 wt. %, Blue/Shade Phthalocyanine Green, 264-8735 available from Sun Chemical) was dispersed into distilled water (70 wt. %) with Acid Green 26 dye

(10 wt. %, Phthalocyanine dye, Basantol™ Green 910, available from BASF Corporation) for 18 minutes on an Eiger™ mill.

Example 10

(COMPARATIVE)

C.I. Pigment Green 7 (35 wt. %, Blue/Shade Phthalocyanine Green, 264-8735 available from Sun Chemical) was dispersed into water (56 wt. %) with an ammonia solubilized styrene/acrylic copolymer (9 wt. %, Joncryl™ 67, available from S.C.

Johnson Polymer) for 18 minutes on an Eiger™ mill.

Example 11

C.I. Pigment Orange 5 (32 wt. %, DNA Orange, 276-0003 available from Sun Chemical) was dispersed into water (52 wt. %) with Acid Orange 142 dye (16 wt. %, Azo/1:2 Cr Orange dye, Basantol™ Orange 270, available from BASF Corporation) for 60 minutes on an Eiger™ mill.

Example 12

(COMPARATIVE)

C.I. Pigment Orange 5 (35 wt. %, DNA Orange, 264-0003 available from Sun Chemical) was dispersed into water (54 wt. %) with an ammonia solubilized styrene/acrylic copolymer (9 wt. %, Joncryl™ 67, available from S.C. Johnson Polymer)

5 for 18 minutes on an Eiger™ mill.

Example 13

C.I. Pigment Red 122 (26 wt. %, Quinacridone Magenta, 228-0122 available from Sun Chemical) was dispersed into distilled water (61 wt. %) with Acid Red 51 dye (13
10 wt. %, Xanthene dye, Basovit™ Red 425E, available from BASF Corporation) for 24 minutes on an Eiger™ mill.

Example 14

C.I. Pigment Red 122 (26 wt. %, Quinacridone Magenta, 228-0122, available
15 from Sun Chemical) was dispersed into distilled water (61 wt. %) with Acid Red 52 dye (13 wt. %, Xanthene dye, Duasyn™ Acid Red B-SF, available from Clariant Corporation) for 24 minutes on an Eiger™ mill.

Example 15

20 C.I. Pigment Red 122 (24 wt. %, Quinacridone Magenta, 228-0122, available from Sun Chemical) was dispersed into distilled water (60 wt. %) with Acid Red 52 dye (16 wt. %, Xanthene dye, Duasyn™ Acid Red B-SF, available from Clariant Corporation) for 24 minutes on an Eiger™ mill.

Example 16

25 C.I. Pigment Red 122 (20 wt. %, Quinacridone Magenta, 228-0122 available from Sun Chemical) was dispersed into distilled water (60 wt. %) with Acid Red 52 dye (10 wt. %, Xanthene dye, Duasyn™ Acid Red B-SF, available from Clariant Corporation) for 24 minutes on an Eiger™ mill.

Example 17

30 C.I. Pigment Red 122 (20 wt. %, Quinacridone Magenta, 228-0122 available from Sun Chemical) was dispersed into distilled water (70 wt. %) with Reactive Red 180 dye (10 wt. %, Monoazo dye, Duasyn™ Brilliant Red F3B-SF, available from Clariant
35 Corporation) for 18 minutes on an Eiger™ mill.

Example 18

C.I. Pigment Red 81 (24 wt. %, Yellow/Shade Rhodamine, SMA Salt 228-9862 available from Sun Chemical) was dispersed into distilled water (70 wt. %) with Direct Red 253 dye (6 wt. %, Direct dye, SANDOVOC-L™ Red 3BF Liquid, available from Clariant Corporation) for 18 minutes on an Eiger™ mill.

Example 19

(COMPARATIVE)

C.I. Pigment Red 122 (36 wt. %, Quinacridone Magenta, 228-0122 available from Sun Chemical) was dispersed into water (57 wt. %) with an anionic phosphosphate ester surfactant (7 wt. %, Phosphac 5534, available from Mfg. Chemical) for 18 minutes on an Eiger™ mill.

Example 20

C.I. Pigment Yellow 14 (20 wt. %, AAOT Diarylide Yellow, 274-1744 available from Sun Chemical) was dispersed into distilled water (70 wt. %) with Acid Yellow 194 dye (10 wt. %, Acid Yellow dye, Basantol™ Yellow 210, available from BASF Corporation) for 36 minutes on an Eiger™ mill.

Example 21

C.I. Pigment Yellow 14 (32 wt. %, AAOT Diarylide Yellow, 274-1788 available from Sun Chemical) was dispersed into distilled water (52 wt. %) with Acid Yellow 36 (16 wt. %, Acid Yellow dye, Basacid™ Yellow 234 available from BASF Corporation) for 18 minutes on an Eiger™ mill.

Example 22

C.I. Pigment Yellow 14 (26 wt. %, AAOT Diarylide Yellow, 274-1744 available from Sun Chemical) was dispersed into water (68 wt. %) with Direct Yellow 107/132 dye (6 wt. %, Direct Yellow dye, SANDOVOC-L™ Yellow 3GF, available from Clariant Corporation) on an Eiger™ mill for 18 minutes.

Example 23

(COMPARATIVE)

5 C.I. Pigment Yellow 14 (35 wt. %, AAOT Diarylide Yellow, 274-1744 available from Sun Chemical) was dispersed into water (56 wt. %) with ammonia solubilized styrene/acrylic copolymer (9 wt. %, Joncryl™ 67, available from S.C. Johnson Polymer)
10 on an Eiger™ mill for 18 minutes.

Example 24

C.I. Pigment Black 7 (26 wt. %, Carbon Black, Regal™ 330, available from Cabot Corporation) was dispersed into distilled water (61 wt. %) with Acid Black 194 dye (13
15 wt. %, Azo/1:2 Cr dye, Basantol™ X80, available from BASF Corporation) for 24 minutes on an Eiger™ mill.

Example 25

C.I. Pigment Black 7 (14 wt. %, Carbon Black, Regal™ 330, available from Cabot Corporation) was dispersed into distilled water (79 wt. %) with Direct Black 168 dye (7
20 wt. %, Polyazo Black dye, Duasyn™ Direct Black HEF-SF liquid, available from Clariant Corporation) for 18 minutes on an Eiger™ mill.

Example 26

25 C.I. Pigment Black 7 (20 wt. %, Carbon Black, Regal™ 330, available from Cabot Corporation) was dispersed into distilled water (70 wt. %) with Reactive Black 31 dye (10 wt. %, Disazo, Copper Complex, Duasyn™ KRL-SF, available from Clariant Corporation) for 18 minutes on an Eiger™ mill.

Example 27

30 C.I. Pigment Black 7 (20 wt. %, Carbon Black, Raven™ 5000 Ultra, available from Columbian Carbon) was dispersed into distilled water (70 wt. %) with Reactive Black 31 dye (10 wt. %, Disazo, Copper Complex, Duasyn™ KRL-SF, available from Clariant Corporation) for 18 minutes on an Eiger™ mill.
35

Example 28

C.I. Pigment Black 7 (20 wt. %, Carbon Black, Regal™ 350R, available from Cabot Corporation) was dispersed into distilled water (70 wt. %) with Reactive Black 31 dye (10 wt. %, Disazo, Copper Complex, Duasyn™ KRL-SF, available from Clariant Corporation) for 18 minutes on an Eiger™ mill.

Example 29

(COMPARATIVE)

C.I. Pigment Black 7 (22 wt. %, Carbon Black, Regal™ 330, available from Cabot Corporation) was dispersed into distilled water (62 wt. %) with a surfactant (7 wt. %, Rhodafac™ BP-769 surfactant, available from Rhone Poulenc), a second surfactant Maracarb™ N-1 (4 wt. %, available from Lignotech) and polyethylene glycol (5 wt. %, PEG-400) on an Eiger™ mill for 18 minutes.

The milling of the pigment to produce the pigment dispersions of this invention in each case was performed on an Eiger™ mill (Eiger is a trademark of Eiger Machinery Corporation, Chicago, IL) having glass milling media of 1 mm in diameter. Each pigment was milled from 6 to 60 minutes at a temperature preferably ranging from 70 to 90° F. Particle size measurements were carried out using a Microtrac™ UPA 150 (available from the Honeywell Corporation, Clearwater, FL). The particles sizes of these inks were measured at the initial time of blending and after two and later six weeks of oven aging at 120 degrees F. Select black dispersions were formulated into prototypic ink jet systems at 5 % total dye and pigment color level and the remainder clear. The clear was distilled water or a 50/50 blend of distilled water and propylene glycol/PEG-400.

Color strength was measured either by reduction with a standard white pigment in a suitable medium or by measuring the pigmentation level required to give a standard-depth print at a specified film thickness. The surface tension was measured with water, having a surface tension value of 72 dynes, as a reference. Color strength was measured tintorially (either visually or quantitatively with a color computer).

Example 13 (dye/pigment) was compared to Example 19 (pigment only) in a tint for

5 shade and color strength. At equal colorant levels, Example 13 was much cleaner to Example 19, and measured 270% strong spectrally to Example 13.

Finally, the jettability of the pigment dispersion was evaluated using an HP-670C thermal ink jet printer (available from Hewlett Packard Corporation, Palo Alto, CA).

10 Jettability was demonstrated with Example 24. A typical ink jet ink was made containing distilled water and humectant, along with the dispersion of Example 24. The prototypic ink was jetted using a Hewlett-Packard Deskjet™ 670C printer with a HP51629A cartridge. The ink jetted well with no clogging of the nozzles. Excellent optical density of the black was demonstrated.

15 Pulp paper handsheets were made by using paper making equipment and by adding standard fixatives, sizing additive and retention aids; additives that are commonly used in paper coloration using both pigments and direct dyes. Handsheets were made by using blue (Example 2) and by using yellow (Example 22) dispersion colorants. Excellent coloration was found with very little color found in the wastewater.

20 Lightfastness depends upon the properties of the pigment and the dye, but should be intermediate between the pigment and the dye for the combined colorant. In the case of a dye with very good lightfastness, such as Acid Black 194; and a pigment with outstanding lightfastness, such as Carbon Black it is found that the optical density change does not decrease (as a function of time) upon exposure in a Xenon
25 Fadeometer.

Tables I to VI provide the results of the analysis of the above physical properties for the pigment dispersions prepared in Examples 1 to 29. All particle size data is reported in nanometers, and tabulated as mean volume (mv), and the percentage of particles having a particle size below a certain minimum (10%) and maximum (90%)
30 size. In Table I it is noted that 90 % of the particles were less than 800 nanometers in size. The particle sizes of the resulting dispersions are generally similar to those of conventional pigment dispersions. However, in some cases, even smaller particle sizes were achieved. Table II provides the data for the particle sizes of various carbon blacks dispersed with dyes. As indicated, very small particle sizes are obtained. Table III
35 provides data for Example 26 and comparative Example 29. Table IV below provides

5 optical density data on some prototype ink compositions made with the pigment
dispersions from Examples 25, 26 and 29 from above. The ink compositions were
made with 5% total (dye and pigment) color by weight and the remainder of a 50/50
blend of distilled water and propylene glycol. The inks were then applied with a #3
Mayer rod on typical copier or ink jet grade paper. Optical density was measured with a
10 densitometer (Byk Gardner). In Table VI optical density data for an ink display made
from the dispersion of Example 24 is presented.

Table I
Colored Dyes and Colored Pigments

		-----Particle Size (nm)-----		
Pigment	Example	MEAN (mv)	MIN (10%)	MAX (90%)
20 Blue 15:3	1	199.6	69.9	348.5
Blue 15:3	2	203.0	98.7	334.6
Blue 15:3	3	213.2	89.4	402.0
Blue 15:3	4	295.6	144.9	475.2
Blue 15:3	5	242.8	136.0	322.5
25 Blue 15:3	6	358.1	192.6	587.3
Blue 15:3	7	326.0	157.8	567.1
Blue 15:3	8 (Comparative)	245.5	71.6	404.5
<hr/>				
Green 7	9	455.5	186.0	766.8
30 Green 7	10 (Comparative)	308.2	144.6	525.9
<hr/>				
Orange 5	11	443.0	152.4	549.9
Orange 5	12 (Comparative)	446.8	194.9	792.4
<hr/>				
35 Red 122	13	172.6	73.0	265.7

5	Red 122	14	473.0	130.2	785.4
	Red 122	15	214.9	110.8	349.3
	Red 122	16	245.5	154.6	348.6
	Red 122	17	362.2	180.1	576.2
	Red 81	18	173.0	66.7	306.4
10	Red 122	19 (Comparative)	138.7	49.7	246.0
<hr/>					
	Yellow 14	20	120.6	52.1	206.7
	Yellow 14	21	258.8	82.9	443.1
	Yellow 14	22	415.5	136.5	481.4
15	Yellow 14	23 (Comparative)	261.7	128.7	351.5

Table IICarbon Black Dispersions

-----Particle Size (nm) -----

20	<u>Pigment</u>	<u>Example</u>	<u>MEAN(mv)</u>	<u>MIN(10%)</u>	<u>MAX(90%)</u>
----	----------------	----------------	-----------------	-----------------	-----------------

5	Regal 330	24	98.7	45.0	161.4
	Regal 330	25	111.4	54.0	179.1
	Regal 330	26	108.5	60.8	159.1
	Raven 5000 Ultra	27	84.0	29.5	187.4
	Regal 350R	28	183.0	116.5	262.1
10	Regal 330	29 (Comparative)	158.5	95.6	228.3

Table IIICarbon Black/Black Dye Dispersions

	<u>Example</u>	<u>Ink System</u>	----- Particle Size Data (mv) -----		
			<u>Initial</u>	<u>2 Weeks</u>	<u>6 Weeks</u>
15	26	water	108.5	108.9	108.6
	26	water/prop. glycol(1/1)	117.0	133.8	134.6
	26	water/PEG-400(1/1)	98.7	164.3	209.1
	29 (Comparative)	water	158.5	142.5	139.3
20	29 (Comparative)	water/prop. glycol(1/1)	153.4	137.7	134.6
	29 (Comparative)	water/PEG-400(1/1)	154.4	155.5	449.9

Table IVOptical Density of Select Black Prototype Inks

<u>Example</u>	<u>Optical Density</u>
25	1.21
26	1.31
29 (Comparative)	0.90

Table VSurface Tension (dynes/cm)

<u>Color</u>	<u>Example</u>	<u>Surface Tension</u>
Yellow	22	57.7
Yellow	23 (Comparative)	40.0
Blue	4	62.4
Blue	8 (Comparative)	42.5

Table VI

<u>Time in Fadeometer (hours)</u>	<u>Optical Density</u>
0 — Initial	2.16
24	2.14
48	2.15
72	2.17
162	2.13

The pigment dispersions prepared in accordance with the teachings of the present invention indicate excellent quality of dispersion as quantified by: particle size, particle size stability, high color value and high optical density, excellent dispersion and ink stability. Higher surface tension is found with dispersing with dye than with conventional resins or surfactants. Improved lightfastness over dyes is observed. Additionally, the compositions of the present invention have the ability to jet in an ink jet print head (when made into a prototypical ink jet ink) and have the ability to color paper

- 5 efficiently without much loss of color due to effluent waste.

Those skilled in the art having the benefit of the teachings of the present invention as hereinabove set forth, can effect numerous modifications thereto. These modifications are to be construed as being encompassed within the scope of the present invention as set forth in the appended claims.

5 We claim:

1. An aqueous based pigment dispersion comprising a pigment, dye and water, wherein the pigment is dispersed into the dye.

2. The pigment dispersion of Claim 1 wherein the pigment is selected from
10 carbon black pigments; phthalocyanine blue pigments; phthalocyanine green pigments; diarylide yellow pigments; azo orange pigments; monoarylide yellow pigments; naphthol red pigments; rhodamine red pigments; precipitated azo pigments; benzimidazolone pigments; heterocyclic yellow pigments; carbazole violet pigments; oxide pigments; and quinacridone pigments.

15 3. The pigment dispersion of Claim 2 wherein the pigment is a carbon black pigment selected from various grades of C.I. Pigment Black 7.

4. The pigment dispersion of Claim 2 wherein the pigment is a phthalocyanine blue pigment selected from C.I. Pigment Blue 15, C.I. Pigment Blue 15:1, C.I. Pigment Blue 15:2, C.I. Pigment Blue 15:3, C.I. Pigment Blue 15:4, C.I.
20 Pigment Blue 15:6, and C.I. Pigment Blue 16.

5. The pigment dispersion of Claim 2 wherein the pigment is a phthalocyanine green pigment selected from C.I. Pigment Green 7, and C.I. Pigment Green 36.

6. The pigment dispersion of Claim 2 wherein the pigment is a diarylide
25 yellow pigment selected from C.I. Pigment Yellow 14, C.I. Pigment Yellow 12, C.I. Pigment Yellow 17, C.I. Pigment Yellow 13, and C.I. Pigment Yellow 83.

7. The pigment dispersion of Claim 2 wherein the pigment is an azo orange pigment selected from C.I. Pigment Orange 5, C.I. Pigment Orange 13, C.I. Pigment Orange 16, C.I. Pigment Orange 34, and C.I. Pigment Orange 36.

30 8. The pigment dispersion of Claim 2 wherein the pigment is a monoarylide yellow pigment selected from Pigment Yellow 1, C.I. Pigment Yellow 3, C.I. Pigment Yellow 74, C.I. Pigment Yellow 73, C.I. Pigment Yellow 75, and C.I. Pigment Yellow 65.

9. The pigment dispersion of Claim 2 wherein the pigment is a naphthol red pigment selected from C.I. Pigment Red 22, C.I. Pigment Red 23, C.I. Pigment Red 17,
35 C.I. Pigment Red 210, C.I. Pigment Red 170, C.I. Pigment Red 188, C.I. Pigment Red

5 185, C.I. Pigment Red 146, C.I. Pigment Red 144, and C.I. Pigment Red 176.

10. The pigment dispersion of Claim 2 wherein the pigment is a rhodamine red pigment selected from C.I. Pigment Red 81:1, C.I. Pigment Red 81:2, C.I. Pigment Red 81:3, and C.I. Pigment Red 81:5.

11. The pigment dispersion of Claim 2 wherein the pigment is a precipitated
10 azo pigment selected from C.I. Pigment Red 48:1, C.I. Pigment Red 48:2, C.I. Pigment Red 48:3, C.I. Pigment Red 49:1, C.I. Pigment Red 49:2, and C.I. Pigment Red 57:1.

12. The pigment dispersion of Claim 2 wherein the pigment is a benzimidazolone pigment selected from C.I. Pigment Yellow 151, C.I. Pigment Yellow 154, and C.I. Pigment Yellow 180.

15 13. The pigment dispersion of Claim 2 wherein the pigment is a heterocyclic yellow pigment selected from C.I. Pigment Yellow 138, C.I. Pigment Yellow 139, C.I. Pigment Yellow 93, C.I. Pigment Yellow 109, C.I. Pigment Yellow 110 and C.I. Pigment Yellow 128.

14. The pigment dispersion of Claim 2 wherein the pigment is the carbazole
20 violet pigment C.I. Pigment Violet 23.

15. The pigment dispersion of Claim 2 wherein the pigment is an oxide pigment selected from C.I. Pigment Black 11, C.I. Pigment Blue 29, C.I. Pigment Blue 27, C.I. Pigment Green 17, C.I. Pigment Green 18, C.I. Pigment Red 101, and C.I. Pigment Yellow 42.

25 16. The pigment dispersion of Claim 2 wherein the pigment is a quinacridone pigment selected from C.I. Pigment Violet 19, C.I. Pigment Red 122, C.I. Pigment Red 202, C.I. Pigment Red 206, and C.I. Pigment Red 207.

17. The pigment dispersion of Claim 1 wherein the dye is selected from acid dyes, natural dyes, direct dyes, basic dyes, and reactive dyes.

30 18. The pigment dispersion of Claim 17 wherein the dye is an acid dye.

19. The pigment dispersion of Claim 18 wherein the acid dye is selected from a yellow acid dye, an orange acid dye, a red acid dye, a violet acid dye, a blue acid dye, a green acid dyes, and a black acid dye.

20. The pigment dispersion of Claim 19 wherein the yellow acid dye is
35 selected from Acid Yellow 1 (C.I. 10316); Acid Yellow 7 (C.I. 56205); Acid Yellow 17

5 (C.I. 18965); Acid Yellow 23 (C.I. 19140); Acid Yellow 29 (C.I. 18900); Acid Yellow 36 (C.I. 13065); Acid Yellow 42 (C.I. 22910); Acid Yellow 73 (C.I. 45350); Acid Yellow 99 (C.I. 13908); Acid Yellow 194; and Food Yellow 3 (C.I. 15985).

21. The pigment dispersion of Claim 19 wherein the orange acid dye is selected from Acid Orange 1 (C.I. 13090/1); Acid Orange 10 (C.I. 16230); Acid Orange
10 20 (C.I. 14603); Acid Orange 76 (C.I. 18870); Acid Orange 142; Food Orange 2 (C.I. 15980); and Orange B.

22. The pigment dispersion of Claim 19 wherein the red acid dye is selected from Acid Red 1 (C.I. 18050); Acid Red 4 (C.I. 14710); Acid Red 18 (C.I. 16255); Acid Red 26 (C.I. 16150); Acid Red 27 (C.I. 16185); BASOVITTM 425E (available from BASF
15 Corporation) a xanthene based acid dye also known as Acid Red 51 (C.I. 45430); Acid Red 52 (C.I. 45100); Acid Red 73 (C.I. 27290); Acid Red 87 (C.I. 45380); Acid Red 94 (C.I. 45440); Acid Red 194; and Food Red 1 (C.I. 14700).

23. The pigment dispersion of Claim 19 wherein the violet acid dye is selected from Acid Violet 7 (C.I. 18055); and Acid Violet 49 (C.I. 42640).

20 24. The pigment dispersion of Claim 19 wherein the blue acid dye is selected from include Acid Blue 1 (C.I. 42045); Acid Blue 9 (C.I. 42090); Acid Blue 22 (C.I. 42755); Acid Blue 74 (C.I. 73015); Acid Blue 93 (C.I. 42780); and Acid Blue 158A (C.I. 15050).

25 25. The pigment dispersion of Claim 19 wherein the green acid dye is selected from Acid Green 1 (C.I. 10028); Acid Green 3 (C.I. 42085); Acid Green 5 (C.I. 42095); Acid Green 26 (C.I. 44025); and Food Green 3 (C.I. 42053).

26. The pigment dispersion of Claim 19 wherein the black acid dye is selected from Acid Black 1 (C.I. 20470); Acid Black 194.

27. The pigment dispersion of Claim 17 wherein the dye is a direct dye.

30 28. The pigment dispersion of Claim 27 wherein the direct dye is an anionic direct dye.

29. The pigment dispersion of Claim 27 wherein the direct dye is a cationic direct dye.

30 30. The pigment dispersion of Claim 27 wherein the direct dye is selected from Direct Blue 86 (C.I. 74180), Direct Blue 199, Direct Black 168, Direct Red 253 and
35

5 Direct Yellow 107/132.

31. The pigment dispersion of Claim 17 wherein the dye is a reactive dye.

32. The pigment dispersion of Claim 31 wherein the reactive dye is selected from Reactive Yellow 37; Reactive Black 31; Reactive Blue 77, Reactive Red 180 and Reactive Red 108.

10 33. The pigment dispersion of Claim 1 containing about 1 wt. % to about 50 wt.% dye, based on the weight of the composition.

34. The pigment dispersion of Claim 33 wherein the dye is about 3 wt. % to about 25 wt.%.

15 35. The pigment dispersion of Claim 1 containing about 1 wt. % to about 50 wt.% pigment, based on the weight of the composition.

36. The pigment dispersion of Claim 35 wherein the pigment about 5 wt. % to about 50 wt.%.

37. A printing ink composition comprising the aqueous based pigment dispersion of Claim 1.

20 38. A method for preparing an aqueous based pigment dispersion comprising dispersing a pigment into a dye and water.

39. A method for preparing a printing ink composition comprising adding the aqueous based pigment dispersion of Claim 1 to a conventional printing ink formulation.

25

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 99/11935

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C09D11/00 C09B67/22 C09B67/20

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C09B C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 710 706 A (TOYO INK MANUF. CO.LTD.) 8 May 1996 (1996-05-08) claim 1; examples 1-19	1,2,9, 14-17
A	EP 0 259 130 A (ING. C. OLIVETTI) 9 March 1988 (1988-03-09) examples	1,37
A	DE 23 39 029 A (ICI) 14 February 1974 (1974-02-14) page 1, paragraph 1 page 1, paragraph 2 -page 3, paragraph 2 page 8, line 16 -page 11, paragraph 2 page 12, paragraph 3 -page 13, paragraph 1 -/-	1,2

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

4 October 1999

Date of mailing of the international search report

19/10/1999

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3018

Authorized officer

Ketterer, M

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/11935

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 97 35927 A (BASF AG) 2 October 1997 (1997-10-02) page 1, line 16 -page 2, line 17 page 12, line 8 - line 28 claim 1; examples -----	1,2,17
E	EP 0 859 036 A (SCITEX DIGITAL PRINTING, INC.) 19 August 1998 (1998-08-19) example 1 -----	1,2,17
A	EP 0 385 330 A (BASF AKTIENGESELLSCHAFT) 5 September 1990 (1990-09-05) page 3, line 42 -page 4, line 9 page 7, line 25 - line 33 -----	1,17
A	EP 0 517 513 A (CIBA GEIGY AG) 9 December 1992 (1992-12-09) column 1, line 10 - line 21 column 2, line 13 - line 24 -----	1,2,6, 17,18,37
A	DATABASE WPI Week 8506 Derwent Publications Ltd., London, GB; AN 1985-034404 XP002117499 K. HIROMITSU ET. AL.: "Dyestuff dispersing agent" & JP 59 227951 A (TOYO INK MFG. CO.), 21 December 1984 (1984-12-21) abstract -----	1,17,37
A	EP 0 538 784 A (HOECHST AG) 28 April 1993 (1993-04-28) abstract; examples -----	1,17

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PC/US 99/11935

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 710706	A	08-05-1996	JP 8127749 A US 5635552 A	21-05-1996 03-06-1997
EP 259130	A	09-03-1988	IT 1195146 B DE 3785276 A DE 3785276 T JP 2519744 B JP 63086768 A US 4836852 A	12-10-1988 13-05-1993 21-10-1993 31-07-1996 18-04-1988 06-06-1989
DE 2339029	A	14-02-1974	GB 1424517 A BE 803088 A FR 2194752 A IT 1003115 B JP 49132109 A NL 7310507 A	11-02-1976 31-01-1974 01-03-1974 10-06-1976 18-12-1974 05-02-1974
WO 9735927	A	02-10-1997	CN 1214715 A EP 0889934 A	21-04-1999 13-01-1999
EP 859036	A	19-08-1998	CA 2227669 A JP 10310733 A	14-08-1998 24-11-1998
EP 385330	A	05-09-1990	DE 3906525 A DE 59009075 D JP 2269775 A JP 2924973 B US 5344465 A	06-09-1990 22-06-1995 05-11-1990 26-07-1999 06-09-1994
EP 0517513	A	09-12-1992	DE 69213830 D DE 69213830 T DK 517513 T ES 2092041 T JP 6088037 A US 5306342 A	24-10-1996 13-03-1997 07-10-1996 16-11-1996 29-03-1994 26-04-1994
JP 59227951	A	21-12-1984	JP 1742694 C JP 4009192 B	15-03-1993 19-02-1992
EP 538784	A	28-04-1993	CA 2081146 A DE 59206108 D ES 2088070 T JP 5311090 A US 5264032 A	24-04-1993 30-05-1996 01-08-1996 22-11-1993 23-11-1993